

X0007

N-Channel Enhancement Mode MOSFET

30V(VDS) / ± 20 V(VGS) / 150A(ID)

Rev1.6



Wafer Specification

1. Order Information

Part No.	Description	Gross die / per 8" wafer
X0007	30V(V_{DS}) / $\pm 20V(V_{GS})$ / 150A(I_D) N-Channel Enhancement Mode MOSFET	6,756


2. Mechanical Data

Nominal Back Metal Composition, Thickness	Ti-Ni-Ag (13kÅ°)
Nominal Front Metal Composition, Thickness	AlCu (4µm)
Wafer Diameter	200mm, with 010 notch
Wafer Thickness	150µm±10µm
Scribe Line Width	60µm
Passivation	SiN+SiO ₂

3. Key Electrical Characteristics of Die (at $T_J = 25^\circ\text{C}$, unless otherwise specified)

Parameter	Description	Min.	Typ.	Max.	Unit	Test Conditions
$V_{(BR)DSS}$	Drain-to-Source Breakdown Voltage	30			V	$V_{GS}=0V$, $I_D=250\mu A$
$I_{D(Device\ Ref)}$	Continuous Drain Current			150	A	$T_J=25^\circ\text{C}$
$R_{DS(on)}(CP)$	Static Drain-to-Source On-Resistance		2.5	7	mΩ	$V_{GS}=10V$, $I_D=1A$
			3.9	9	mΩ	$V_{GS}=4.5V$, $I_D=1A$
$R_{DS(on)}(FT)$	Static Drain-to-Source On-Resistance		2.6	2.8	mΩ	$V_{GS}=10V$, $I_D=30A$
			4.0	5.5	mΩ	$V_{GS}=4.5V$, $I_D=20A$
$V_{GS(th)}$	Gate Threshold Voltage	1.2	1.7	2.2	V	$V_{DS}=V_{GS}$, $I_D=250\mu A$
I_{DSS}	Drain-to-Source Leakage Current			1	µA	$V_{DS}=30V$, $V_{GS}=0V$
I_{GSS}	Gate-to-Source Leakage Current			± 100	nA	$V_{GS}=\pm 20V$, $V_{DS}=0V$
T_J, T_{STG}	Operating and Storage Temperature	-55°C to 150°C Max				

4. Die Outline

	Die Size: 2375µm × 1789µm (including scribe line)
	Gate: 284µm × 431µm
	For TO-252 package Suggest Bonding wire: Gate: 1 × 1.7 mil Cu Source: 2 × 15 mil Al