

X0074

N-Channel Enhancement Mode MOSFET

30V(VDS) / ± 20 V(VGS) / 4A(ID))

Rev0.2



Wafer Specification

1. Order Information

Part No.	Description	Gross die / per 8" wafer
X0074	30V(V_{DS}) / $\pm 20V(V_{GS})$ / 4A(I_D) N-Channel Enhancement Mode MOSFET	80,394


2. Mechanical Data

Nominal Back Metal Composition, Thickness	Ti-Ni-Ag(13kÅ°)
Nominal Front Metal Composition, Thickness	AlCu (4µm)
Wafer Diameter	200mm, with 010 notch
Wafer Thickness	150µm±10µm
Scribe Line Width	60µm
Passivation	SRO+SiN

3. Key Electrical Characteristics of Die (at $T_J = 25^\circ\text{C}$, unless otherwise specified)

Parameter	Description	Min.	Typ.	Max.	Unit	Test Conditions
$V_{(BR)DSS}$	Drain-to-Source Breakdown Voltage	30			V	$V_{GS}=0V$, $I_D=-250\mu A$
$I_{D(Devic\ Ref)}$	Continuous Drain Current			4	A	$T_J=25^\circ\text{C}$
$R_{DS(on)}(CP)$	Static Drain-to-Source On-Resistance		28	37	mΩ	$V_{GS}=10V$, $I_D=1A$
			44	64	mΩ	$V_{GS}=4.5V$, $I_D=1A$
$R_{DS(on)}(FT)$	Static Drain-to-Source On-Resistance		29	38	mΩ	$V_{GS}=10V$, $I_D=4A$
			45	65	mΩ	$V_{GS}=4.5V$, $I_D=3A$
$V_{GS(th)}$	Gate Threshold Voltage	1.0	1.5	2.5	V	$V_{DS}=V_{GS}$, $I_D=250\mu A$
I_{DSS}	Drain-to-Source Leakage Current			1	µA	$V_{DS}=30V$, $V_{GS}=0V$
I_{GSS}	Gate-to-Source Leakage Current			±100	nA	$V_{GS}=\pm 20V$, $V_{DS}=0V$
T_J, T_{STG}	Operating and Storage Temperature	-55°C to 150°C Max				

4. Die Outline

	Die Size: 624µm × 583µm (including scribe line)
	Gate: 130µm × 130µm
	For SOT23 package Suggest Bonding wire: Gate: 1 × 1.0 mil Cu Source: 5 × 1.65 mil Cu